


Biophysics in dentistry

Dóra Haluszka



17/04/2023

The structure of tooth





Structure of enamel

- highly mineralized, hardest substance in the human body
- transparent (dentin)
- hydroxyapatite 90%, carbonates, water, organic material
- does not contain collagen
- morphology: ameloblast – enamel rods, enamel prisms
- 4 μm diameter
- the long axis of the enamel rod is perpendicular to the underlying dentin
- acellular, avascular



<https://pocketdentistry.com/4-enamel/#c4-fig-0001>




https://pocketdentistry.com/4-enamel/#R_c4-fig-0013


https://pocketdentistry.com/4-enamel/#R_c4-fig-0007

Structure of dentin

- calcified tissue
- 70% minerals, 20% organic material—collagen, 10% water
- does not contain cells
- 3-5 mm thickness
- color of tooth
- types: primary, secondary, and tertiary
- structure: tubules, intertubular dentin, peritubular dentin
- it decays more rapidly
- dentin accumulation in tubules





<https://www.sciencedirect.com/science/article/pii/S1359646219305688>



<https://www.dentin.co/new-blog/2017/6/9/dental-hypersensitivity-hydrodynamic-theory>

The hierarchical structure of collagen

No turnover!!!



Non-enzymatic glycation of collagen fibers






Figure 1: The initial stage of glycation resulting in the formation of a Schiff base and an Amadori product (Voziyan, and Hudson 2005).




Matsuda Y, Miura J, Shimizu M, Aoki T, Kubo M, Fukushima S, Hashimoto M, Takeshige F, Araki T. Influence of Nonenzymatic Glycation in Dentinal Collagen on Dental Caries. *J Dent Res.* 2016 Dec;95(13):1528-1534.

Methods

What techniques can help us answering scientific questions?

Scanning electron microscopy (SEM)



Two-photon microscopy




LG
green channel
490-560 nm
LR
red channel
600-700 nm

MaiTai Deep Sea Laser

Tunable range: 700-1400 nm
Frequency: 80 MHz
Impulse lenght: 100 fs
Average power: 3 W

Atomic force microscopy (AFM)



others...



Scanning electron microscopy (SEM)

What can be examined?


1. Surface structures – plaque formation
2. „Dental wear”
3. Effectiveness of surface treatments

SEM


TEM




Ultrastructure of dental plaques





web of extracellular matrix material, rod-shaped cells



swollen rod morphology: TM7 phlyium (t), Spirochaeta bacteria (s), arrows – membrane-associated vesicles




Ultrastructure of dental plaques II



arrow: open tubules, broken arrow: extensive web of extracellular strands, short rod-shaped microorganisms,

v: vesicles, c: cells

Ultrastructure of dental plaques III




yellow: bacterial plaque



Dental plaque, biofilm (400x)

Blue: colony of coccid bacteria, red: RBC




<https://www.telegraph.co.uk/news/picturegalleries/howaboutthat/11067916/Plaque-attack-Close-up-images-of-teeth-reveal-what-lives-in-your-mouth.html>

Types of dental wear


loss of mineralized tissue unrelated to bacterial action

1. **Erosion (chemical)**: dissolution of dental tissue caused by acidic agents (extrinsic and intrinsic factors) food, drinks, reflux, bulimia, anorexia
2. **Abrasion (mechanical)**: interaction between teeth and exogenous objects: toothpicks, dental floss, toothpastes, toothbrushes (hard bristles, too much pressure is applied when brushing)
3. **Attrition (mechanical)**: caused by excessive functional or parafunctional forces and bruxism
4. **Abfraction (mechanical)**: when the tooth is subjected to extreme stress and fatigue

Abfraction and attrition of enamel




enamel abfraction: multiple cavities, partially overlapping furrows




enamel attrition: scratches, stripes, and striations


Lesions of dentin



In advanced lesions, there is clear dentin exposure with remains of the smear layer on the surface.



In advanced lesions the dentin is covered with crystallized debris.





In erosion lesions, the tubules have rounded openings; the collagen matrix between them is eroded and demineralized.

Two-photon microscopy


What can be examined?

1. autofluorescence and second harmonic generated signal from organic components of dentin (e.g. collagen) under normal and pathological conditions



2. Structure, orientation and periodicity of collagen fibers


Second-harmonic generation (SHG, also called frequency doubling) is a nonlinear optical process in which two photons with the same frequency interact with a nonlinear material, are "combined", and generate a new photon with twice the energy of the initial photons (equivalently, twice the frequency and half the wavelength), that conserves the coherence of the excitation.



Tunable range: 700-1400 nm
Frequency: 80 MHz
Impulse lenght: 100 fs
Average power: 3 W

Normal dentin-enamel junction (DEJ)

Bright-field




a

D

10 μm

2PEF



E


D



b


10 μm

SHG



E

D



c



10 μm

autofluorescence – organic
components (E + D)


SHG signal only in dentin
– presence of collagen

The SHG/2PEF ratio can be a sensitive parameter to monitor caries development

SoproLife camera – 450 nm






sound dentin



T: tubulus


caries dentin



Decrease in fluorescence lifetime of dentin by ageing/glycation



In sound dentin the aromatic amino acids of collagen have longer fluorescence lifetime.
(0 week)

Due to glycation the accumulated autofluorescent glycated endproduct (pentosidine) dominates with shorter lifetime(6 weeks).




Detection of dentinal collagen glycation by using Fluorescence in Vivo Imaging (FOBI) system

Incubation of demineralized tooth sections in ribose solution –
aim: determination the extent of glycation/accumulation of AGEs




**exc: 450 nm
em: 525 nm**



As a result of glycation both the AF and SHG signal intensity increased


Conclusions:

- there is no enzymatic degradation (compared to caries)
- The collagen orientation did not change, thus, the accumulation of AGEs may have led to the higher emitted SHG signal



As a result of glycation the length of collagen fibers increased between dental tubules





SHG images



Atomic force microscopy (AFM)


What can be examined?

1. Topography: structure of surfaces, roughness (e.g. effects of surface treatments)
2. Mechanics: Young' modulus of demineralized dentinal collagen (e.g. diabetes)




Glycation increased the roughness of intertubular dentin




control



ribose




Force curve – force map




$$F = \frac{4}{3} E^* R^{1/2} d^{3/2}$$

E = complex Young's modulus of the system
R = radius of curvature of AFM tip
d = indentation depth



Glycation caused higher stiffness in ribose group

control




MPa

45.0
20.0
-5.00


MPa

-5.00



10,6 ± 4,71 MPa

ribose




MPa

45.0
20.0
-5.00

MPa



-5.00




36,62 ± 23,15 MPa

Effect of various surface treatments to enamel roughness


enamel slices without surface treatment




air-polished with a 54-μm particle size
calcium carbonate prophylactic powder (5 s)



air-polished with a 54-μm particle size calcium
carbonate prophylactic powder (10 s)



rubber diamond polisher



polishing brush with built-in
silicon carbide abrasive particles